




96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 10/28/2011	Completed: 10/28/2011	Letter: J	rb	P.O.#:	Test Report #:	2-89824-0-
Client's Identification	10oz PVC Scrim Banner Mesh. Width: 38". Finish: Matte. Weight: 10oz.					
Tested For: Rob Pinedo			Key Test: NFPA 701-2010 TM#2 Fold			310
Pitman Co. 21908 E. Valley Blvd City of Industry, CA 91789			Tel: 1-(888)-274-1451		Ext: 2896	
			Fax: 1-(909)-595-1451			
PC: 1H						
TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Folded Specimens						
TEST CONFIGURATION: <input checked="" type="checkbox"/> Single Layer; <input type="checkbox"/> Multi Layer						
RESULTS REPORTED: <input checked="" type="checkbox"/> Initially <input type="checkbox"/> After 72 hours water leaching						
<input type="checkbox"/> After 3 dry cleanings <input type="checkbox"/> After 100 hours accelerated weathering						
<input type="checkbox"/> After 5 launderings @ 160°F						
RESULTS:						
Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)			
1	0	0	130			
2	0	0	153			
3	0	0	139			
4	0	0	147			
APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 272 g/m ²						
FAILURE CRITERIA: For each individual specimen --						
Afterflame	Drip Burn	Char Length				
Exceeds 2.0 Seconds	Exceeds 2 seconds	Exceeds 1,050 mm (41.34")				
RETEST PROVISION: Test 2 additional specimens if only 1 specimen fails.						
CONCLUSION: Based on the above Results and Failure criteria, the item tested:						
<input checked="" type="checkbox"/> Passes; <input type="checkbox"/> Fails; <input type="checkbox"/> Requires testing of 2 additional specimens						
CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Folded Specimens.						
 AUTHORIZED SIGNATURE THE GOVMARK ORGANIZATION, INC. / ec			NOV 04 2011			
MS. PHYLLIS PETTIT			(Page 1 of 2)			

File Copy



96-D Allen Boulevard
Farmingdale, New York 11735-5626 USA
Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956
e-mail: info@govmark.com

Received: 10/28/2011 Completed: 10/28/2011 Letter: J rb P.O.#: Test Report #: 2-89824-0-

Client's Identification: 10oz PVC Scrim Banner Mesh. Width: 38". Finish: Matte. Weight: 10oz.

Tested For: **Rob Pinedo** Key Test: NFPA 701-2010 TM#2 Fold 310
Pitman Co. Tel: 1-(888)-274-1451 Ext: 2896
21908 E. Valley Blvd Fax: 1-(909)-595-1451
City of Industry, CA 91789

PC: 1H

TEST PERFORMED: NFPA 701 - Standard Methods of Fire Tests for Flame Propagation of Textiles and Films - 2010 Edition - Test Method #2 - Folded Specimens

TEST CONFIGURATION: Single Layer; Multi Layer

RESULTS REPORTED: Initially After 72 hours water leaching
 After 3 dry cleanings After 100 hours accelerated weathering
 After 5 launderings @ 160°F

RESULTS:

Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)	Char Length (mm)
1	0	0	130
2	0	0	153
3	0	0	139
4	0	0	147

APPROXIMATE WEIGHT OF MATERIAL (as measured by Govmark): 272 g/m²

FAILURE CRITERIA: For each individual specimen --

Afterflame	Drip Burn	Char Length
Exceeds 2.0 Seconds	Exceeds 2 seconds	Exceeds 1,050 mm (41.34")

RETEST PROVISION: Test 2 additional specimens if only 1 specimen fails.

CONCLUSION: Based on the above Results and Failure criteria, the item tested:

Passes; Fails; Requires testing of 2 additional specimens

CERTIFICATION: I certify that the above results were obtained after testing specimens in accordance with the procedures and equipment specified by NFPA 701 - 2010 Edition Test Method #2 Folded Specimens.

Phyllis Pettit NOV 04 2011

AUTHORIZED SIGNATURE
THE GOVMARK ORGANIZATION, INC. / ec

MS. PHYLLIS PETTIT

(Page 1 of 2)