



96-D Allen Boulevard Farmingdale, New York 11735-5626 USA Tel. +1 (631) 293-8944 Fax +1 (631) 293-8956 e-mail: testing@govmark.com

Page 1

Received: 10/16/2017 C	ompleted: 10/18/2017 I	Letter: V BG	P.O.#:	Test Report #:	3-21743-0-
Client's Style: Do Thickness				. Composition: Polyester/PVC. Weight	: 9 oz/sqm.
Tested For: Gary Yor			Ke	y Test: NFPA 701-2015 TM#2 Flat	475
	hics Drive Center 3 rk, NJ 07407-1325			Tel: 1-(201)-440-2500 Ext Fax: 1-()	:
LE:2015 NE:2019	V:01/15 NTR 04	/16		PC:1H	
	FPA 701 - Standard est Method #2 - Fl			Flame Propagation of Textile	s and Films
SPECIMEN CONFIGURA	TION: [x] Single	Layer; [] Mult	i Layer		
RESULTS REPORTED:	<pre>[x] Initially [] After 3 dry o [] After 5 laund</pre>	_		72 hours water leaching 100 hours accelerated weathe	ring
RESULTS:					
Length Specimen #	Afterflame (seconds)	Drip Burn (seconds)		Char Length (mm)	
1	0	0		170	
2	0	0		170	
3	0	0		160	
4	0	0		150	
5	0	0		130	
6	0	0		1.45	
7	0	0		170	
8 9	0	0		140	
10	Ö	0		175 145	
APPROXIMATE WEIGHT	OF MATERIAL (as m	easured by Govma	ark): 296	g/m²	
	For each individu				
Afterflame	Drip	Burn	Cha 	r Length 	
Exceeds 2.0 sec	onds Exce	eds 2.0 seconds	Exc	eeds 435 mm (17.1")	
RETEST PROVISION:	Test 5 additional	specimens if or	nly 1 speci	men fails.	
CONCLUSION: Based	on the above Resu	lts and Failure	Criteria,	the item tested:	
[x] Passes; [] Fails; [] Requ	ires testing of	5 addition	al specimens	
		(Page 1 of 2)			